Proceedings of the ASME 2018 Conference on Smart Materials, Adaptive Structures and Intelligent Systems SMASIS 2018 September 10–12, 2018, San Antonio, TX, USA

SMASIS2018-8245

DRAFT: NUCLEOS: TOWARD RAPID-PROTOTYPING OF ROBOTIC MATERIALS THAT CAN SENSE, THINK AND ACT

Mustafa Ayad

Collaborative Robotics Lab School of Engineering Technology Purdue University West Lafayette, Indiana 47907 Email: mayad@purdue.edu

Robert Nawrocki School of Engineering Technology Purdue University West Lafayette, Indiana 47907 Email: robertnawrocki@purdue.edu

Richard M. Voyles

Collaborative Robotics Lab School of Engineering Technology Purdue University West Lafayette, Indiana 47907 Email: rvoyles@purdue.edu

Junseok Lee Collaborative Robotics Lab School of Engineering Technology Purdue University West Lafayette, Indiana 47907 Email: lee2839@purdue.edu

Hyowon Lee Weldon School of Biomedical Engineering School of Engineering Technology Birck Nanotechnology Center Purdue University West Lafayette, Indiana 47907 Email: hwlee@purdue.edu

Daniel Leon-Salas Purdue University West Lafavette, Indiana 47907 Email: wleonsal@purdue.edu

ABSTRACT

Robotic Materials are materials that have sensing, computation and, possibly actuation, distributed throughout the bulk of the material. In such a material, we envision semiconducting polymer based sensing, actuation, and information processing for on-board decision making to be designed, in tandem, with the smart product that will be implemented with the smart material. Prior work in printing polymer semiconductors for sensing and cognition have focused on highly energetic inkjet printing. Alternatively, we are developing liquid polymer extrusion processes to work hand-in-hand with existing solid polymer extrusion processes (such as Fused Deposition Manufacturing - FDM) to simultaneously deposit sensing, computation, actuation and structure at the same time. We demonstrate the successful extrusion printing of conductors and capacitors to impedance-match a new, higher-performance organic transistor design that solves the cascading problem of the device previously reported and is more amenable to liquid extrusion printing. Consequently, these printed devices are integrated into a sheet material that is folded into a 3-D, six-legged walking machine with attached electric motor.

INTRODUCTION

A common definition of robotics is "systems that combine perception, cognition and actuation"; hence, they can sense, think and act. In general, we design such systems using a lumped model whereby sensors, computers and actuators are components of the system in a design process that is discrete and siloed in nature. In other words, mechanical design, electrical design, software design, and control design, are all considered separately, as in robotic systems described in [1, 2]. The new field of "soft robotics" combines the function of sensors, actuators, and structure into compliant materials that appear "soft" upon interaction with the environment [3], yet, these systems are still designed primarily in the same siloed way.

Robotic Materials are materials that have sensing, computation and, even actuation, distributed throughout the bulk of the material, adding entirely new characteristics to the selection of



FIGURE 1. CONCEPTUAL VIEW OF THE CRITICAL COMPONENTS OF THE 3-D POLYMER PRINTER FOR SMART PRODUCTS

materials for the design of smart products. The complexity of the resulting design space—we predict—will revolutionize design, demanding an end to siloed design practices. These materials will largely be polymer-based, 3-D printed and will evolve in concert with the artifacts they will enable; ushering in a new era in co-design of smart products from "designer polymers."

The synthesis of polymers around World War II enabled a new era for the types of things designers could design. More recently, the 3-D printing revolution democratized prototyping by removing the knowledge barrier designers needed to produce an instantiation of their design. But neither of these innovations had a direct impact on the design process, itself. The way designers design was not changed. We believe the age of robotic materials will usher in a new golden era of design in which materials and products will be designed holistically with unified design methods that integrate both form and function across the hardware/software interface. This will enable the advancement of co-design to fully embrace the convergence of electrical, mechanical, and software design.

This paper represents an important step in our prior work

on lithography-based Structured Computational Polymers [4], an all-polymer form of robotic materials, for the rapid and masscustomizable realm of low-cost 3-D printing of entire smart products. Building on our neuromorphic architecture implemented from polymer electronic materials [5, 6], we have demonstrated the first results of a four-year project to bring fully-integrated robotic materials to life with potentially low-cost additive manufacturing. While we report here only passive devices converted to 3-D printing, the range of devices we have previously demonstrated include transistors, memristive devices, sensors and actuators that span the full range of devices necessary to realize the neuromorphic circuits for user-defined robotic materials.

Over the years, several researchers have developed active and passive 3-D printed electronic components using inkjet printing technology [7]. While many of these efforts have produced impressive results, we believe the energetics of inkjet printing of polymer semiconducting devices and the coffee ring effect are not good for long-term success with high-performance devices. At the micro-level, inkjet-printed semiconducting devices look like the "craters on the moon" with planarity levels that produce passable but sub-optimal films insufficient for high-performance transistors and other components [8, 9]. Alternatively, we are developing liquid polymer extrusion processes to work hand-inhand with existing solid polymer extrusion processes, such as FDM, to simultaneously deposit sensing, computation, actuation and structure at the same time.

This paper is an extension of the prior work which constructed synthetic neurons with lithography [4] or with discrete components [10] to make robotic materials, or structured computational polymers. We extend this prior work along the lines of [11], which explored the preparation of a printable substrate through planarization and subsequent spraying of conductive materials. Here, we report on early results of a new, highlyintegrated project [Fig. 1] to produce a complete 3-D printer that will eventually produce complete smart products containing distributed sensing, neural computation and actuation throughout the bulk of formed material without the use of inkjet printing that produces suboptimal films. We also demonstrate the successful extrusion-printing of capacitors to match the impedance to a new, higher-performance organic transistor design that solves the cascading problem of the device previously reported and is more amenable to liquid extrusion printing. Finally, the electronics are integrated into a sheet of composite materials, which can be folded into a six-legged walking robot similar to the design of Fearing [12].

PRIOR WORK

The prior papers reported on 1-D and 2-D materials for actuation and computation using polymers as the flexible constituents. Semiconducting, conducting, and ferroelectric polymers have been used as sensors and actuators for contraction and expansion [13–15]. Also, several groups in the soft robotics space have demonstrated complete robotics systems based on polymers [16, 17]. there also reported the biomimetic jellyfish robot [18] created with an ionic polymer metal composite and an all-polymer foot [19] capable of climbing walls, mimicking the ability of a gecko or spider foot. However, the proposed designs concentrate only on the sensing ability of their material and do not address cognition nor actuation aspects. As such, our proposal differs starkly with the aforementioned designs. Recently a number of research groups have demonstrated fabrication of "electronic skin" from polymeric materials [20, 21]. However, the these designs typically concentrate only on the sensing ability of their material and do not address cognition nor actuation aspects. Additionally, they are typically fabricated using lithographic processes. As such our proposal differs starkly with the aforementioned designs.



FIGURE 2. (a-d) PLARIZATION PROCESS (a) CORNROWS (b) PLANARIZATION (c) POLYMER ELECTRONICS (d) MULTIPLE PRINTING (e-g) SURFACE CHARACTERISTICS (e) SCANNED SURFACE (f) HEIGHTS OF A SCAN (g) LEVELED AND UNLEVELED SURFACE. SCALE BAR: 1 mm

COMPONENT CAPABILITIES

As mentioned previously, the point of this paper is to report initial efforts to pave the way for 3-D printing of entire smart products. These include the planarization of solid extrusion of (thermoplastic) structural layers, the smoothing of parallel liquid extrusions, the liquid extrusion of multilayer capacitors, and the performance of a low-impedance organic transistor capable of cascading signals from one stage to the next.

Substrate Preparation

A side-effect of the thermoplastic 3-D printing process are the "corn rows" of adjacent extrusions that occur, as in Fig. 2(a) and (e). The solid extrusion fuses enough in the "four-connected sense" (top, bottom, right, left) to form a rigid material with about 75% of the strength of native material. Yet, the surface roughness is extremely low for polymer electronics as it provides no uniformity for the semiconducting films. A StrataSys FDM machine exhibits a surface roughness of about 70 μ m). We have demonstrated that we can smooth this type of surface with the polymer CyEPL, to the degree necessary for high-quality poly-



FIGURE 3. (a) TRANSISTOR STRUCTURE (b) AMPLIFICATION [23]

mer electronics: a planarity of 1–2 µm [22].

We demonstrated this with a StrataSys Dimension Elite FDM machine by printing a flat substrate, as shown in Fig. 2(b). Multiple layers were deposited to develop a thermally stable substrate. The native level of surface flatness is shown by a profilometer Fig. 2(f). Figure 2(g) illustrates the boundary between the planarizing CyEPL polymer (left) and the bare ABS material (right). The dramatic smoothing is evident at the edge of the material and the profilometry shows planarity with CyEPL as good as $1.69 \,\mu$ m. Finally, the process is repeated with *n* structural layers and *m* intelligence layers. The area of planning for these complex layers and their interaction is both a subject of development for this project and for future research.

Line Smoothing

As mentioned above, inkjet printing is a highly energetic process that we feel is not capable of producing the highest quality thin films. We have chosen a different and more generic approach that is derived directly from a process common in polymer electronics: blade coding. In our process, we locally blade coded the viscous layers into a uniform thin film by physically smoothing with a rigid blade at the local level. As an example, we smoothed the corn rows that result from liquid extrusion of polymer semiconductors, as shown in Fig. 2(b).

Fig. 2(c) and (g) demonstrates the ability of local blade coding to maintain precise, localized films using an Ultimus V precision dispenser and Nordson robotic stage. The dispenser laid five adjacent rows of PMMA and then we used our prototype microactive doctor blade to smooth the corn rows of a $3 \,\mu m$ film. The resulting profilometer plot is revealing a surface roughness of 100 nm.

Transistor Performance

We have previously fabricated a prototype of low voltage, p-type double-gate organic field effect transistors (OFET) using



FIGURE 4. THE RESPONSE OF THE TRANSISTOR TO ILLUMI-NATION: 2.4nA (DARK). 71nA (BRIGHT)

dinaphtho[2,3-b:2',3'-f]thieno[3,2-b]thiophene (DNTT) through a conventional lithographic process [23, 24] The device structure was composed of Parylene 60 nm, Au 30 nm, Parylene 60 nm, DNTT 30 nm, Au 30 nm, Parylene 60 nm, and Au 30 nm [Fig. 3(a)]. This transistor is also used for amplification [Fig. 3(b)]. The fabrication process included thermally evaporated gold source, drain, and gate electrodes, as well as the organic semiconductor. CVD-deposited biocompatible Parylene served as the dielectric, as well as top and bottom encapsulation and substrate layers. The channel length of width of the p-type devices were 5 μ m and 10 μ m, respectively. The transistor is tested with and without light, showing different response to illumination [Fig. 4].

Printed Capacitors

A capacitor consists of two plates (electrodes) enclosing a dielectric. Capacitor layout is shown in Fig. 5(a). Here, the capacitor electrodes are printed using the a solid extrusion FDM printer with PE873 Stretchable Silver Conductor (DuPont, USA) for printed electronics purposes. The dielectric of the capacitors is PE773 Stretchable Encapsulant for Wearables (DuPont, USA) and was printed using the same printer. The capacitors are printed as shown in Fig. 5(b). The capacitance was in the range of 52-58 pF with an active area of 25 mm².

NUCLEOs ROBOTIC SMART PRODUCT

NUCLEOs (NeUromorphic Computing on Laminated Electronic Organic substrate) is a six-legged walking robot built out of sheets of laminated, single-layer robotic materials that are folded into shape and driven by an attached motor [Fig. 6] (2-D printed). As a proof-of-concept, we built a NUCLEOs circuit out



FIGURE 5. A PRINTED CAPACITOR. SCALE BAR: 10 mm



FIGURE 6. NUCLEOs PAPERBOT

of the lithography-fabricated organic transistor that acts as a phototransistor and connected it to the external motor driver circuit. As shown in Fig. 4, when the transistor is unbiased ($V_{gs} = 0$), the difference in the drain currents under dark and bright conditions are around 30 times. A transresistance circuit built of operational amplifiers to amplify the change in the drain currents and convert it to voltage to control the transistor driving the motor. With this circuit, the motor to drive NUCLEOs turns off without illumina-



FIGURE 7. PAPERBOT UNDER LIGHT

tion and turns on under illumination [Fig. 7], effectively allowing NUCLEOs to chase a light spot.

CONCLUSION

Robotic Materials are materials that combine sensing, computation and actuation, distributed throughout the bulk of the material. This adds entirely new characteristics to the selection of materials for the design of smart products. We demonstrate the successful extrusion printing of capacitors to impedance-match a new, higher-performance organic transistor design that solves the cascading problem of the device previously reported and is more amenable to liquid extrusion printing. Therefore, these printed devices are integrated into a sheet material that is folded into a 3-D, six-legged walking machine with attached electric motor.In summery, robotic materials will mostly be polymer-based, 3-D printed and will evolve in concert with the artifacts they will enable; a new era in co-design of smart products from designer polymers.

ACKNOWLEDGMENT

This work was sponsored in part by the NSF under grants CNS-1726865 and CNS-1439717 with additional support from the NSF Center for Robots and Sensors for the Human well-Being (RoSe-HUB). We also would like to acknowledge help from Bryan Boudouris, Purdue University, fabrication work of Takao Someya, University of Tokyo, and lab work of Taylor Zigon, Purdue University.

REFERENCES

- Voyles, R., and Larson, A., 2005. "TerminatorBot: A novel robot with dual-use mechanism for locomotion and manipulation". *IEEE/ASME Transactions on Mechatronics*, *10*(1), feb, pp. 17–25.
- [2] Kaneko, K., Harada, K., Kanehiro, F., Miyamori, G., and Akachi, K., 2008. "Humanoid robot HRP-3". In 2008 IEEE/RSJ International Conference on Intelligent Robots and Systems, IEEE.
- [3] Albu-Schaffer, A., Eiberger, O., Grebenstein, M., Haddadin, S., Ott, C., Wimbock, T., Wolf, S., and Hirzinger, G., 2008. "Soft robotics". *IEEE Robotics & Automation Magazine*, 15(3), sep, pp. 20–30.
- [4] Nawrocki, R. A., Yang, X., Shaheen, S. E., and Voyles, R. M., 2011. "Structured computational polymers for a soft robot: Actuation and cognition". In 2011 IEEE International Conference on Robotics and Automation, IEEE.
- [5] Nawrocki, R. A., Voyles, R. M., and Shaheen, S. E., 2014. "Neurons in polymer: Hardware neural units based on polymer memristive devices and polymer transistors". *IEEE Transactions on Electron Devices*, 61(10), oct, pp. 3513–3519.
- [6] Nawrocki, R. A., Galiger, E. M., Ostrowski, D. P., Bailey, B. A., Jiang, X., Voyles, R. M., Kopidakis, N., Olson, D. C., and Shaheen, S. E., 2014. "An inverted, organic WORM device based on PEDOT:PSS with very low turn-on voltage". *Organic Electronics*, 15(8), aug, pp. 1791–1798.
- [7] Teichler, A., Perelaer, J., and Schubert, U. S., 2013. "Inkjet printing of organic electronics-comparison of deposition techniques and state-of-the-art developments". *Journal of Materials Chemistry C*, 1(10), pp. 1910–1925.
- [8] Soltman, D., and Subramanian, V., 2008. "Inkjet-printed line morphologies and temperature control of the coffee ring effect". *Langmuir*, 24(5), pp. 2224–2231.
- [9] Kawase, T., Sirringhaus, H., Friend, R. H., and Shimoda, T., 2001. "Inkjet printed via-hole interconnections and resistors for all-polymer transistor circuits". *Advanced Materials*, *13*(21), pp. 1601–1605.
- [10] Voyles, R. M., Abbaraju, P., Leon-Salas, D., Sanjana, S., and Lakshmanan, A., 2016. "Soft robotic skin from intelligent meta-materials". In *Communications in Computer and Information Science*. Springer Singapore, pp. 121–137.
- [11] Falco, A., Petrelli, M., Bezzeccheri, E., Abdelhalim, A., and Lugli, P., 2016. "Towards 3d-printed organic electronics: Planarization and spray-deposition of functional layers onto 3d-printed objects". *Organic Electronics*, 39, dec, pp. 340–347.
- [12] Hoover, A. M., Steltz, E., and Fearing, R. S., 2008. "Roach: An autonomous 2.4 g crawling hexapod robot". In Intelligent Robots and Systems, 2008. IROS 2008. IEEE/RSJ International Conference on, IEEE, pp. 26–33.
- [13] Barisci, J. N., Wallace, G. G., Andrews, M. K., Partridge,

A. C., and Harris, P. D., 2002. "Conducting polymer sensors for monitoring aromatic hydrocarbons using an electronic nose". *Sensors and Actuators B: Chemical*, **84**(2-3), may, pp. 252–257.

- [14] Osada, Y., and De Rossi, D., 1999. Polymer Sensors and Actuators. Macromolecular Systems - Materials Approach. Springer Berlin Heidelberg.
- [15] Ikushima, K., John, S., Yokoyama, K., and Nagamitsu, S., 2009. "A practical multilayered conducting polymer actuator with scalable work output". *Smart Materials and Structures*, 18(9), jul, p. 095022.
- [16] Correll, N., and Voyles, R., 2014. "Robotic materials: From smart polymers to computational metamaterials". In Proc. Robot Makers Workshop, Robotics: Science Systems Conf.
- [17] Polygerinos, P., Correll, N., Morin, S. A., Mosadegh, B., Onal, C. D., Petersen, K., Cianchetti, M., Tolley, M. T., and Shepherd, R. F., 2017. "Soft robotics: Review of fluiddriven intrinsically soft devices; manufacturing, sensing, control, and applications in human-robot interaction". Advanced Engineering Materials.
- [18] Yeom, S.-W., and Oh, I.-K., 2009. "A biomimetic jellyfish robot based on ionic polymer metal composite actuators". *Smart Materials and Structures*, 18(8), jun, p. 085002.
- [19] Kim, S., Spenko, M., Trujillo, S., Heyneman, B., Mattoli, V., and Cutkosky, M. R., 2007. "Whole body adhesion: hierarchical, directional and distributed control of adhesive forces for a climbing robot". In Proceedings 2007 IEEE International Conference on Robotics and Automation, IEEE.
- [20] Someya, T., Sekitani, T., Iba, S., Kato, Y., Kawaguchi, H., and Sakurai, T., 2004. "A large-area, flexible pressure sensor matrix with organic field-effect transistors for artificial skin applications". *Proceedings of the National Academy* of Sciences of the United States of America, 101(27), pp. 9966–9970.
- [21] Wang, C., Hwang, D., Yu, Z., Takei, K., Park, J., Chen, T., Ma, B., and Javey, A., 2013. "User-interactive electronic skin for instantaneous pressure visualization". *Nature Materials*, 12(10), p. 899.
- [22] Nawrocki, R. A., 2014. "Fabrication and application of a polymer neuromorphic circuitry based on polymer memristive devices and polymer transistors". PhD thesis, University of Denver.
- [23] Lee, S., Reuveny, A., Matsuhisa, N., Nawrocki, R., Yokota, T., and Someya, T., 2016. "Enhancement of closed-loop gain of organic amplifiers using double gate structures". *IEEE Electron Device Letters*, pp. 770–773.
- [24] Nawrocki, R. A., Matsuhisa, N., Yokota, T., and Someya, T., 2016. "300-nm imperceptible, ultraflexible, and biocompatible e-skin fit with tactile sensors and organic transistors". *Advanced Electronic Materials*, 2(4), feb, p. 1500452.